



KÖSTER Polysil TG 500

Deeply penetrating primer for damp and salt burdened substrates, immobilizes salts, consolidates sanding substrates

Features

KÖSTER Polysil TG 500 is a thin fluid product based on a polymers and silicates. On salt burdened and on damp substrates it leads to a reduction of the pore volume and decreases the likelihood of new salt efflorescence development. It also increases the chemical and mechanical resistance of mineral building materials. Depending on the substrate, the product penetrates the surface up to 2 cm deep. KÖSTER Polysil TG 500 also has strengthening and hydrophobing properties. The material is compatible with mortars, plasters, cementitious slurries, and concrete.

Technical Data

| | |
|-------------------------|------------------------------|
| Application temperature | min. +5 °C |
| Specific gravity | 1.03 g/cm ³ |
| Surface | transparent, slightly sticky |

Application of next layer:

| | |
|---------------------|-----------------------------------|
| -after 30 minutes | - cementitious building materials |
| -after min 24 hours | - acrylate and silicate paints |

Fields of Application

KÖSTER Polysil TG 500 is used to consolidate, strengthen, and to protect mineral substrates and to reduce their absorbency, even of such problematic building materials as sandstone. KÖSTER Polysil TG 500 decreases the danger of new salt efflorescence development and raises the resistance of mineral substrates to the freeze thaw cycle. All mineral substrates are suited for application except for gypsum. KÖSTER Polysil TG 500 can be used as primer beneath polymer-modified bitumen thick film sealants such as KÖSTER Deuxan 2C and KÖSTER Bikuthan 2C as well as KÖSTER Repair Mortar, KÖSTER Repair Mortar Plus, etc.

Substrate

KÖSTER Polysil TG 500 can be applied to weakly and to strongly absorbant, to dry and to moist substrates. The substrate has to be free of oil and loose particles. Salt efflorescence must be removed by brushing prior to application of KÖSTER Polysil TG 500.

Application

Deeply penetrating priming:

KÖSTER Polysil TG 500 can be brush or spray applied. During the curing time, the surrounding and substrate temperature must not fall below 0 °C. Salts which came through the surface of the substrate during the curing process must be removed by brushing. After full cure, salts will be immobilized in the substrate.

Internal waterproofing using rigid sealing slurries:

In order to install extremely resistant coatings using KÖSTER NB 1 Grey, the substrate is first primed with KÖSTER Polysil TG 500 a minimum of 30 minutes before the application of KÖSTER NB 1 Grey, (without addition of KÖSTER SB-Bonding Emulsion). The second layer of KÖSTER NB 1 Grey can be applied after the first coat has set.

Surface protection:

KÖSTER Polysil TG 500 is sprayed, rolled, or brushed onto the substrate To strengthen and improve the chemical and mechanical resistance of mineral building materials, (Consumption approx. 130 – 250 g/m²). The protective coating reaches its final cure after approximately 16 hours.

Consumption

Approx. 0.1 - 0.25 kg/m² depending on substrate, strongly absorbent substrates may require more.

On strongly absorbent substrates the consumption may be higher.

Cleaning

Clean tools immediately after use with water.

Packaging

| | |
|-----------|----------------|
| M 111 001 | 1 kg bottle |
| M 111 010 | 10 kg jerrycan |

Storage

Store the material cool but frost-free. In originally sealed containers it can be stored for a minimum of 12 months.

Safety

Wear protective gloves and goggles during application. Observe all governmental, state, and local safety regulations when processing the material.

Related products

| | |
|--|----------------------|
| KÖSTER Repair Mortar NC | Prod. code C 535 025 |
| KÖSTER Repair Mortar R4 | Prod. code C 536 |
| KÖSTER Hydrosilicate Adhesive SK | Prod. code M 170 020 |
| KÖSTER Restoration Plaster Grey | Prod. code M 661 025 |
| KÖSTER Restoration Plaster White | Prod. code M 662 025 |
| KÖSTER Restoration Plaster White/Fast | Prod. code M 663 |
| KÖSTER Restoration Plaster White/Light | Prod. code M 664 020 |
| KÖSTER Hydrosilicate Board | Prod. code M 670 |
| KÖSTER NB 1 Grey | Prod. code W 221 025 |
| KÖSTER NB 2 White | Prod. code W 222 025 |
| KÖSTER NB Elastic Grey | Prod. code W 233 033 |
| KÖSTER NB 4000 | Prod. code W 236 025 |
| KÖSTER Bikuthan 2C | Prod. code W 250 028 |
| KÖSTER Deuxan 2C | Prod. code W 252 032 |
| KÖSTER Repair Mortar | Prod. code W 530 025 |
| KÖSTER Repair Mortar Plus | Prod. code W 532 025 |

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of application have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.